

## Mint of the United States at Philadelphia,

ASSAY DEPARTMENT,

August 18<sup>th</sup>, 1884.

Counterfeit Gold Coin (\$5) from  
 Ast. Treas. U.S. Boston.

$\frac{1}{10}$  grain light - Specific Gravity 15.9  
 Thickness about like the others,

Fineness Gold  $805\frac{1}{2}$  Silver 23.

Value (Gold) \$ 4.47, say 4.50.

Resists the acid tests almost as well as  
 genuine,

Reading faulty but very fair

Color very good, a trifle yellowish

Jacob B. Eckfeldt  
 Assayr

NARA RG104, Entry 1, Box 132

Mint of the United States at Philadelphia,  
Assay Department,  
August 18, 1884

Counterfeit Gold Coin (\$5) from  
Ast. Treas. U.S. Boston.  
1/10 grain light specific gravity 15.9  
Thickness about like the others.  
Fineness Gold 805 ½ silver 23.  
Value (gold) \$4.47, say 4.50.  
Resists the acid tests almost as well as genuine.  
Reeding faulty but very fair  
Color very good, a trifle yellowish.

Jacob B. Eckfeldt  
Assayer